

	L #	Hits	Search Text	DBs
1	L1	8951 54	@pd>"20051118"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
2	L2	1864	((523/160) or (523/161)).CCLS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
3	L3	121	1 and 2	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
4	L4	2493	((106/31.6) or (524/556)).CCLS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
5	L5	139	1 and 4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
6	L6	28	(3 5) and ((polymer or resin) near5 emulsion or latex) and (glass adj transition or tg or "t.sub.g") and ink	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
7	L7	41800	hydrophobic adj (substrate or medium or sheet or surface) or (polyvinyl adj chloride or pvc!) near10 (substrate or medium or sheet)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
8	L8	3	6 and 7	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
9	L9	18	(3 5) and ((polymer or resin) near5 emulsion or latex) same (glass adj transition or tg or "t.sub.g") and ink	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
10	L10	386	1 and ((polymer or resin) near5 emulsion or latex) and (glass adj transition or tg or "t.sub.g") and ink	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
11	L11	36	7 and 10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
12	L12	172	1 and ((polymer or resin) near5 emulsion or latex) same (glass adj transition or tg or "t.sub.g") and ink	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
13	L13	214	10 not 12	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
14	L14	2	("5977210").PN.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
15	L15	2	("6239193").PN.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
16	L16	1199	((polymer or resin) near5 emulsion or latex) same (glass adj transition or tg or "t.sub.g") and (inkjet or ink near3 jet)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
17	L17	835	((polymer or resin) near5 emulsion or latex) near10 (glass adj transition or tg or "t.sub.g") and (inkjet or ink near3 jet)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
18	L19	83	16 and 7	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

	L #	Hits	Search Text	DBs
19	L20	412	((polymer or resin) near5 emulsion or latex) near10 (glass adj transition or tg or "t.sub.g") and ink.ti.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
20	L21	269	20 and (glycol or glycol near5 ether or methylpyrrolidone or methyl adj2 pyrrolidone or sulfolane or pyrol)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
21	L22	147	21 and (anionic or nonionic) near5 surfactant	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB